

KSKM SİNER MAGNEZİTLER / KSKM DEAD BUTNT MAGNESİTES

PRODUCT NAMES	CHEMICAL ANALYSIS %						PHYSICAL PROPERTIES	
	MgO	SiO2	CaO	Fe2O3	Al2O3	L. O. I	Bulk Density (gr/cm ³)	Grain Size (mm)
KSKM SİNER MAGNEZİTLER / KSKM DEAD BUTNT MAGNESİTES								
KSKM SS	96.5	0.8	1.7	0.5	0.2	0.2	3.45	0 - 15
KSKM S	96	1.0	1.8	0.5	0.2	0.2	3.40	0 - 15
KSKM GR	96	1.2	1.8	0.5	0.2	0.2	3.40	0 - 15
KSKM SP 1	95	1.5	2.5	0.5	0.2	0.2	3.38	0 - 15
KSKM SP 2	95	2.0	2.0	0.5	0.2	0.2	3.36	0 - 15
KSKM SD	92	1.2	2.0	4.0	0.2	0.2	3.40	0 - 15
KSKM D 1	87	1.2	6.0	5.0	0.2	0.2	3.40	0 - 15
KSKM D2	84	3.0	6.0	5.	0.2	0.2	3.38	0 - 15
KSKM Y	95	2.5	1.5	0.5	0.2	0.2	3.35	0 - 15
KSKM YK 1	94	3.5	1.5	0.5	0.2	0.2	3.34	0 - 15
KSKM YK 2	93	4.0	2.0	0.5	0.2	0.2	3.34	0 - 15
KSKM ST 1	92	4.5	2.0	0.5	0.2	0.2	3.33	0 - 15
KSKM ST 2	91	6.0	2.2	0.5	0.2	0.2	3.33	0 - 15
KSKM ST 3	90	6.0	2.0	0.5	0.2	0.2	3.33	0 - 15
KSKM TP	88	8.0	2.5	1.0	0.2	0.2	3.25	0 - 15
KSKM HB	88	9.0	1.5	0.5	0.2	0.2	3.25	0 - 15